

# Infineum C9425

## Description

Infineum C9425 is a zinc dialkyl dithiophosphate which provides antiwear, antioxidant and anticorrosion protection to crankcase lubricants. Treat rates depend upon application and performance requirements.

## Typical Inspections

Property:	Value <sup>(a)</sup> :	Unit:	Method <sup>(b)</sup> :
Density @ 15 C, kg/m3	1122	kg/m3	ASTM D1298
Flash Point Deg C	95 Minimum	°C	ASTM D93A
Kinematic Viscosity @ 100 C	10.6	cSt	ASTM D445
Kinematic Viscosity @ 40 C	130	cSt	ASTM D445
Mineral Oil	26	%(m)	Calculated
Phosphorus	8.0	%(m)	ASTM D4927
Zinc	8.8	%(m)	ASTM D4927

(a)Not a specification, (b)Methods typically used by Infineum manufacturing plants

## Handling / Precautions

To minimize hydrogen sulfide evolution and/or decomposition:

- Do not blow with wet gas, and prevent any other contact with water.
- Do not heat the product. Facilities should be designed to handle ZDDPs without heating. If heating is necessary, a careful engineering review is essential to ensure that the product is not overheated, as overheating can result in hydrogen sulfide, mercaptan, and olefin evolution due to ZDDP decomposition. If the product is heated, it should be done by hot oil or water systems to, at most, the recommended maximum loading/unloading temperature. Steam at 0 psig (100 deg. C) should only be used if other means are not available and only if the product is agitated sufficiently to avoid high skin temperatures.
- Avoid air contact with the heated product because it may result in discoloration.

Min Load/Unload Temp:	10 °C (50 °F)
Max Load/Unload Temp:	60 °C (140 °F)
Vis @ Min Load/Unload Temp:	1,445 cSt
Vis @ Max Load/Unload Temp:	44 cSt
Minimum Storage Temperature:	10 °C (50 °F)
Maximum Storage Temperature:	40 °C (104 °F)
Do not reheat above:	60 °C (140 °F)

For detailed data please refer to the relevant MSDS.

## Further Information

For further information please contact your local Infineum affiliate or representative.

Version: 14 November 2012 (1.0)

The information contained in this document is based upon data believed to be reliable and relates only to the matters specifically mentioned in this document. Although Infineum has used reasonable skill and care in the preparation of this information as of the date below, in the absence of any overriding obligations arising under a specific contract to supply goods or services, no representation, warranty (express or implied), or guarantee is made as to the suitability, accuracy, reliability or completeness of the information; nothing in this document shall reduce the user's responsibility to satisfy itself as to the suitability, accuracy, reliability, and completeness of such information for its particular use; there is no warranty against intellectual property infringement; and Infineum shall not be liable for any loss, damage or injury that may occur from the use of this information other than death or personal injury caused by its negligence. No statement shall be construed as an endorsement of any product or process. For greater certainty, before use, particularly if the product is used for a purpose or under conditions which are abnormal or not reasonably foreseeable, this information must be reviewed with the supplier.

'Infineum', 'Dobanax', 'Paratrac', 'Synactra', 'Vektron', 'Vistone' and the corporate mark comprising the interlocking ripple device are trademarks of Infineum International Limited.

© Copyright Infineum International Limited (2012). All rights reserved.



<https://www.lubrex.com.tr/>

[lubrex@lubrex.com.tr](mailto:lubrex@lubrex.com.tr)